

**NANO EXPRESS**

**Open Access**

# Trapping Iron Oxide into Hollow Gold Nanoparticles

Chienwen Huang<sup>1</sup>, Jiechao Jiang<sup>1</sup>, Chivarat Muangphat<sup>1</sup>, Xiankai Sun<sup>2</sup>, Yaowu Hao<sup>1\*</sup>

## Abstract

Synthesis of the core/shell-structured Fe<sub>3</sub>O<sub>4</sub>/Au nanoparticles by trapping Fe<sub>3</sub>O<sub>4</sub> inside hollow Au nanoparticles is described. The produced composite nanoparticles are strongly magnetic with their surface plasmon resonance peaks in the near infrared region (wavelength from 700 to 800 nm), combining desirable magnetic and plasmonic properties into one nanoparticle. They are particularly suitable for in vivo diagnostic and therapeutic applications. The intact Au surface provides convenient anchorage sites for attachment of targeting molecules, and the particles can be activated by both near infrared lights and magnetic fields. As more and more hollow nanoparticles become available, this synthetic method would find general applications in the fabrication of core-shell multifunctional nanostructures.

## Introduction

Gold nanoparticles (AuNPs) and superparamagnetic iron oxide nanoparticles (SPIONs) have been subjects of intensive research in the last decade [1,2]. They are generally considered as biocompatible and are of great interest for diagnostic imaging and therapeutic applications. SPIONs are currently being used as magnetic resonance imaging contrast agents in clinic. Heating effect of SPIONs in an alternating magnetic field has been extensively explored for potential hyperthermia treatment of cancer [3]. Biomedical applications of AuNPs originate from their surface plasmon resonance (SPR) effect, a strong enhancement of absorption and scattering of light in resonant with the SPR frequency, which has been utilized for photothermal ablation treatment and optical imaging. To tune the SPR wavelength to the near infrared (NIR) region that is commonly regarded as a 'clear window' for deep tissue penetration of light, various types of Au nanoparticles such as nanorods [4], nanoprisms [5], nanoshells [6,7], and nanocages [8,9] have been developed and investigated.

In recent years, combining SPIONs with Au to form a composite multifunctional nanoparticles has attracted considerable attention [10-14]. To date, the effort has been mostly limited on coating iron oxide particles with

a thin layer of Au, where the Au shell not only provides convenient anchorage sites for functionalization of biomolecules through the well-established Au-thiol conjugation procedure but also protects SPIONs from dissolution and aggregation. However, by such an approach, it is difficult, if not impossible, to tune the SPR wavelengths to the NIR region. Reported core/shell particles usually have their SPR in the visible light range (from 500 to 600 nm), which limits their optical functions for in vivo applications. Here, we report an approach to construct iron-oxide/Au core/shell nanoparticles by trapping iron oxide nanoparticles into hollow AuNPs. Such nanoparticles are magnetic with their SPR peaks in the NIR region (wavelength from 700 to 800 nm).

## Experimental Methods

### Synthesis of Porous Hollow Au Nanoparticles


Synthesis of porous hollow Au nanoparticles (PHAuNPs) was detailed in the reference [15]. The key processes are listed here. The synthesis process was conducted inside a typical three-electrode electrodeposition cell with Ag/AgCl electrode in 3 M NaCl solution as the reference [ $U_{ep} = 0.250$  V vs. standard hydrogen electrode (SHE)] and a platinum mesh as the counter electrode. A stack of two anodic alumina filtration membranes (from Whatman Corp.) with the pore diameter of about 300 nm and thickness of 60  $\mu$ m were used as templates. A 700-nm-thick film of Cu was sputter-deposited to block the pores

\* Correspondence: yhao@uta.edu

<sup>1</sup>Department of Materials Science and Engineering, University of Texas at Arlington, Arlington, TX 76019, USA.

Full list of author information is available at the end of the article

of the bottom membrane, and this acted as the working electrode for electrodeposition. A commercial Au sulfite electrodeposition solution (Techni-Gold 25 ES from Technic Inc.) was used as the electrolyte. The pH of the solution was about 7.0, which was changed to 6.0 by adding 0.4 M Ni sulfamate solution. A potential of 0.80 V (vs. Ag/AgCl reference) was applied to the working electrode using a Princeton Applied Research 273A Potentiostat/Galvanostat, at which hydrogen evolution occurred. As hydrogen molecules diffused into the pores inside the membranes, hydrogen nanobubbles formed on the inner wall surface of the pores. These hydrogen nanobubbles served as templates. The high concentration of hydrogen molecules in the bubble boundary reduced the Au<sup>+</sup> complex ion to form Au clusters. Then, these clusters act as a catalyst to trigger the autocatalytical disproportionation reaction:



As a result, an Au shell forms around the hydrogen bubble. Metal Au evolves from clusters, particles to porous networks, forming PHAuNPs, which adhere to the inner wall surface of the pores inside both (bottom and top) membranes. The PHAuNPs-loaded top membrane was ready for the next step of loading Fe<sub>3</sub>O<sub>4</sub> nanoparticles into these PHAuNPs after being washed by passing deionized water through the membrane several times.

#### Loading Fe<sub>3</sub>O<sub>4</sub> Nanoparticles into PHAuNPs

The formation of Fe<sub>3</sub>O<sub>4</sub> nanoparticles via alkaline precipitation was conducted by following a previously reported procedure [16]. Briefly, anhydrous 5.2 g FeCl<sub>3</sub> (0.032 mol) and 2 g FeCl<sub>2</sub> (0.016 mol) were mixed in 25 ml of DI water containing 0.85 ml of 12.1 N HCl under vigorous stirring. This aqueous solution flew through the PHAuNP-loaded AAO membrane using a vacuum filtration setup, which guarantees all PHAuNPs were wetted with the solution. The membrane was removed from filtration setup and immersed into the solution for additional 30 min. The wet membrane was then transferred into 5 ml of 0.5% NH<sub>4</sub>OH and was allowed to sit for 20 min. The color change to yellow–orange indicates the precipitation of iron oxide particles. After the precipitation, the iron oxide nanoparticles (~10 nm) formed within the membrane were washed away by flowing DI water through the membrane using the vacuum filtration setup. The Fe<sub>3</sub>O<sub>4</sub>/PHAuNPs core/shell nanoparticles were released into water after the dissolution of membrane using 2 M NaOH solution. The particles were cleaned by several cycles of dispersion in DI water followed by centrifugation.

#### Characterization of Fe<sub>3</sub>O<sub>4</sub>/PHAuNPs Core/Shell Nanoparticles

Samples for TEM were made by simply dipping a copper grid into the diluted nanoparticle water suspension. TEM micrographs were taken using a Hitachi H9500 HR-TEM. Absorption spectra of the particle water suspensions were measured using a Perkin-Elmer Lambda 19 UV/VIS/NIR Spectrometer. Hysteresis loop of dried particle powder was measured using a vibrating sample magnetometer.


#### Results and Discussions

Synthesized PHAuNPs feature a sub-25-nm shell with a 50-nm hollow core. The shell is of porous nature with the pore size about 2–3 nm, as measured in the high-resolution transmission electron microscopy (HRTEM) image shown in Figure 1a. These nanoscale pores in the shell allow ions (Fe<sup>2+</sup> and Fe<sup>3+</sup>) to diffuse into the hollow space in the core, where precipitation of Fe<sub>3</sub>O<sub>4</sub> takes place upon the addition of OH<sup>-</sup>. The sizes of precipitated Fe<sub>3</sub>O<sub>4</sub> nanoparticles (5–20 nm) are larger than the pore size, resulting in the trapping of the iron oxide nanoparticles inside the PHAuNPs (Figure 1b).

Figure 2 shows TEM analysis before and after loading of iron oxide nanoparticles. After loading, the hollow core of PHAuNPs is occupied by solid substances. During the precipitation, Fe<sub>3</sub>O<sub>4</sub> nanoparticles also formed outside of PHAuNPs, but TEM micrographs clearly show that no small iron oxide nanoparticles were attached to the PHAuNP surface. This is in agreement with the common notion that iron oxide usually does not stick to the Au surface [11]. Given the very different sizes of PHAuNPs (~100 nm) and non-trapped Fe<sub>3</sub>O<sub>4</sub> nanoparticles (<20 nm), they can be readily separated using centrifugation.

The loading of Fe<sub>3</sub>O<sub>4</sub> to the core of PHAuNPs was confirmed by energy-dispersive X-ray (EDS) analysis of one single particle and the selected area electron diffraction (SAED) pattern from three particles. EDS shows the coexistence of Au and Fe in a single particle (Figure 3a, Cu peak is from the TEM grid). The low intensity of Fe may be due to the shield effect of the thick Au shell. The SAED pattern is a superposition of Au and Fe<sub>3</sub>O<sub>4</sub> lattices (Figure 3b), showing three distinguishable planes of (311), (511), and (731) from Fe<sub>3</sub>O<sub>4</sub>. Other Fe<sub>3</sub>O<sub>4</sub> planes overlap with Au planes.


Shown in Figure 4a is the appearance of a bottle of particle water suspension. The cyan color indicates that the suspension absorbs red light. The absorption spectrum is shown in Figure 4b, which has a broad peak centering at 750 nm. This absorption peak corresponds to the SPR wavelength. Compared to PHAuNPs before loading iron oxide, the absorption spectrum shows little



**Figure 1** a and b HRTEM micrographs of PHAuNPs, showing the hollow core and the porous shell with pore size about 2–3 nm.


change. For core/shell nanoparticles, it is well known that the SPR wavelength is dependent on the refractive indices of medium, shell and core. Changing core material usually causes a shift of the SPR wavelength. However, PHAuNPs have a relatively thick shell (>20 nm).

Through a three-dimensional finite difference time domain (FDTD) simulation (using a commercial software from Lumerical Inc), we have proved that at this thickness, the red-shifts of SPR peaks are mainly caused by their surface roughness, and the hollow nature of these particles plays only a minor role [17]. The simulation results show that SPR peaks for hollow particles are only slightly red-shifted compared to solid particles with the same outer diameter (100 nm). For particles with a roughness of 5 nm, SPR peak shifts to longer wavelength (~630 nm). As the roughness increases to 8 nm which is the average grain size in the shell, a much greater red-shift (to 720 nm) is observed. This roughness effect is due to the strong interaction of electric fields from adjacent bumps on the surface, similar to the plasmonic properties of the aggregates of several nanoparticles. The simulated results are in good agreement with experimental results. This unique SPR tuning mechanism makes it possible to maintain the optical properties of PHAuNPs even after the loading of iron oxide.



**Figure 2** TEM micrographs of PHAuNPs before a and b loading iron oxide nanoparticles.

As shown in Figure 4a, the particles can be dragged toward a permanent magnet, unequivocally indicating the magnetic characteristics of the Au nanoparticles. Hysteresis loop of dried particle powder is shown in Figure 4c. Since the  $\text{Fe}_3\text{O}_4$  nanoparticles synthesized using the above-mentioned method are normally smaller than 20 nm, we expect to see a typical superparamagnetic behavior: zero remanence, zero coercivity, and a large saturation field. The small hysteresis shown in the measurement may reflect the presence of some large  $\text{Fe}_3\text{O}_4$  nanoparticles (>30 nm) inside PHAuNPs. Given the size of the hollow space (>50 nm) and the thickness of the porous shell (25 nm), the inward diffusion of  $\text{OH}^-$



**Figure 3** a EDS spectrum of one single particle, showing the coexistence of Au and Fe. b SAED pattern from three particles, showing a superposition of Au and Fe<sub>3</sub>O<sub>4</sub> lattices.

ions may be partially obstructed, resulting in a much slower nucleation rate. As such, the inside particles could grow large. The measured high saturation field is in consistency with the superparamagnetic characteristic. This suggests a mixture of superparamagnetic and ferromagnetic nanoparticles. Ferromagnetic nanoparticles are usually undesirable for bioapplications because of their agglomeration caused by magnetic attraction. However, for iron oxide nanoparticles-loaded PHAuNPs, the thick Au shell can effectively separate them far apart to avoid such magnetic aggregation.

## Conclusion

We have shown that the core/shell-structured Fe<sub>3</sub>O<sub>4</sub>/Au nanoparticles can be synthesized by trapping Fe<sub>3</sub>O<sub>4</sub> nanoparticles inside hollow Au nanoparticles. Because the resulted composite nanoparticles combine the desirable magnetic and plasmonic properties into one nanoentity, they are particularly suitable for in vivo diagnostic and therapeutic applications, where the Au surface provides anchorage sites for attachment of functional molecules and the particles can be activated by both NIR light and magnetic field. As more and more hollow nanoparticles become available, we believe that this synthetic method would find general applications in the fabrication of core-shell multifunctional nanostructures.

## Acknowledgements

This work was supported by the National Science Foundation (ECCS-0901849), the Texas Higher Education Coordinating Board Norman Hackerman Advanced Research Program, and the USAMRMC Prostate Cancer Research Program (W81XWH-05-1-0592). We thank the Characterization Center for Materials and Biology (CCMB) at University of Texas at Arlington for providing financial and technical support for the electron microscopic characterization of the nanoparticles.

## Author details


<sup>1</sup>Department of Materials Science and Engineering, University of Texas at Arlington, Arlington, TX 76019, USA. <sup>2</sup>Department of Radiology and Advanced Imaging Research Center, University of Texas Southwestern Medical Center at Dallas, Dallas, TX 75390, USA.

Received: 22 July 2010 Accepted: 9 September 2010

Published: 28 September 2010

## References

- Boisselier E, Astruc D: *Chem Soc Rev* 2009, **38**:1759-1782.
- Duguet E, Vasseur S, Mornet S, Devoisselle JM: *Nanomedicine* 2006, **1**:157-168.
- Hergt R, Dutz S, Muller R, Zeisberger M: *J Phys Condes Matter* 2006, **18**: S2919-S2934.
- Jana NR, Gearheart L, Murphy CJ: *J Phys Chem B* 2001, **105**:4065-4067.
- Millstone JE, Park S, Shuford KL, Qin LD, Schatz GC, Mirkin CA: *J Am Chem Soc* 2005, **127**:5312-5313.



**Figure 4** The plasmonic and magnetic properties of the Fe<sub>3</sub>O<sub>4</sub>-loaded PHAuNPs. a Appearance of a bottle of particle water suspension. The particles can be dragged toward a permanent magnet. b Absorption spectrum of the particle water suspension, showing a broad peak centering at 750 nm. c Hysteresis loop of dried particle powder, showing that the suspension consists of a mixture of superparamagnetic and ferromagnetic nanoparticles.

6. Gobin AM, Lee MH, Halas NJ, James WD, Drezek RA, West JL: *Nano Lett* 2007, **7**:1929-1934.
7. Lal S, Clare SE, Halas NJ: *Acc Chem Res* 2008, **41**:1842-1851.
8. Sun YG, Xia YN: *Science* 2002, **298**:2176-2179.
9. Chen J, Saeki F, Wiley BJ, Cang H, Cobb MJ, Li ZY, Au L, Zhang H, Kimmey MB, Li XD, Xia Y: *Nano Lett* 2005, **5**:473-477.
10. Xu ZC, Hou YL, Sun SH: *J Am Chem Soc* 2007, **129**:8698.
11. Shevchenko EV, Bodnarchik MI, Kovalenko MV, Talapin DV, Smith RK, Aloni S, Heiss W, Alivisatos AP: *Adv Mater* 2008, **20**:4323-4329.
12. Chiang IC, Chen DH: *Adv Funct Mater* 2007, **17**:1311-1316.
13. Levin CS, Hofmann C, Ali TA, Kelly AT, Morosan E, Nordlander P, Whitmire KH, Halas NJ: *Acs Nano* 2009, **3**:1379-1388.
14. Bardhan R, Chen WX, Perez-Torres C, Bartels M, Huschka RM, Zhao LL, Morosan E, Pautler RG, Joshi A, Halas NJ: *Adv Funct Mater* 2009, **19**:3901-3909.
15. Huang CW, Jiang JC, Lu MY, Sun L, Meletis EI, Hao YW: *Nano Lett* 2009, **9**:4297-4301.
16. Kang YS, Risbud S, Rabolt JF, Stroev P: *Chem Mater* 1996, **8**:2209.
17. Huang C, Hao Y: *J Nanoscience Nanotechnology*.

doi:10.1007/s11671-010-9792-x

**Cite this article as:** Huang *et al*: Trapping Iron Oxide into Hollow Gold Nanoparticles. *Nanoscale Res Lett* 2011 **6**:43.

**Submit your manuscript to a SpringerOpen<sup>®</sup> journal and benefit from:**

- Convenient online submission
- Rigorous peer review
- Immediate publication on acceptance
- Open access: articles freely available online
- High visibility within the field
- Retaining the copyright to your article

---

Submit your next manuscript at ► [springeropen.com](http://springeropen.com)

---